

Sun Control Window Films

Prestige Series

PR 90 Exterior

CLEARLY SUPERIOR



PR 90 Exterior Benefits:


- Good heat rejection provides energy savings and enhanced comfort
- High Visible Light Transmission
- High Visual Clarity
- High Luminous Efficacy
- Non-metalized film, means no signal interference, no edge sealing on vertical applications, and no chance of corrosion
- Reduces air conditioning costs
- Stay cooler by reducing excessive heat in warmer months
- Excellent film for skylight applications, retail store fronts and hard to reach installations
- Hydrophobic hard coat helps to keep the exterior surface of the glass look cleaner
- · Reduces the risk of thermal fracture
- Extends the life and vibrancy in the fabric of furniture and carpets by rejecting a large portion of the UV rays
- Reduces injury risk from flying glass

Performance Results:*

| Visible Light Transmitted | 88% | | | |
|---|-------|--|--|--|
| Total Solar Energy Rejected | 36% | | | |
| TSER—On 60°Angle | 36% | | | |
| Infrared Rejected | 97% | | | |
| Visible Light Reflected Int. | 9% | | | |
| Visible Light Reflected Ext. | 9% | | | |
| UV Rejected | 99.9% | | | |
| Glare Reduction | 1% | | | |
| Luminous Efficacy | 1.4 | | | |
| *Performance based upon 1/4 clear glass | | | | |

IR rejection measured from 900-1000 mm

Interior View



Prestige Series

PR 90 Exterior

CLEARLY SUPERIOR







| Glass Type (All 1/4") | Single Pane Clear | Single Pane Tinted | Double Pane Clear | Double Pane Tinted |
|--|-------------------------|--------------------------|-------------------------|--------------------------|
| Visible Light Transmitted | 88% | 53% | 78% | 47% |
| Total Solar Energy Rejected | 36% | 50% | 45% | 60% |
| Total Solar Energy Rejected — On 60° Angle | 45% | 56% | 54% | 64% |
| Infrared Rejected* | 97% | 97% | 97% | 97% |
| Visible Light Reflected Int. | 9% | 6% | 16% | 13% |
| Visible Light Reflected Ext. | 9% | 6% | 15% | 9% |
| UV Rejected | 99.9% | 99.9% | 99.9% | 99.9% |
| Solar Heat Gain Coefficient | 0.64 | 0.50 | 0.56 | 0.41 |
| U Value | 1.02 | 1.02 | 0.47 | 0.47 |
| Luminous Efficacy | 1.4 | 1.1 | 1.4 | 1.2 |



3M